

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 59-074107

(43)Date of publication of application : 26.04.1984

(51)Int.Cl.

C08F 36/06

C08F 4/70

(21)Application number : 57-183749

(71)Applicant : UBE IND LTD

(22)Date of filing : 21.10.1982


(72)Inventor : MAEHARA NOBUNORI  
UTADA NORIBUMI  
ODA YASUSHI  
ASHITAKA HIDETOMO  
ISHIKAWA HIDEO

## (54) PRODUCTION OF REINFORCED POLYBUTADIENE RUBBER

### (57)Abstract:

**PURPOSE:** To obtain the titled rubber of excellent properties, by completely removing carbon disulfide used as a component of a 1,2 polymerization catalyst.

**CONSTITUTION:** 1,3-Butadiene is mixed with an inert organic solvent. To this mixture a cis-1,4 polymerization catalyst comprising a Co compound and an organoaluminum compound of formula I (wherein R is a 1W6C alkyl or the like; X is a halogen; and n is 1.5W2) is added to form 1,4-polybutadiene (5). A 1,2- polymerization catalyst comprising carbon disulfide, a Co compound and an arganoaluminum compound of formula II is added to the above polymerization reaction mixture, and 1,3-butadiene is polymerized to obtain the final polybutadiene rubber having a boiling n-hexane-insoluble portion of 5W30wt% and a boiling n-hexane-soluble portion of 95W70wt% (6). After adding a polymerization short-stop, the



solid polybutadiene rubber is separated and recovered, and then the carbon disulfide is separated by distillation and/or adsorption to obtain the titled rubber substantially free from carbon disulfide.